



# STATIC SHIELDING BAG SELECTION CHART

Product Details	Metal-In Static Shielding <a href="#">1000 Series</a>	Metal-In Static Shielding <a href="#">1300 Series</a>	Metal-Out Static Shielding <a href="#">1500 Series</a>	Metal-Out Cushioned Static Shielding <a href="#">2120R Series</a>
<b>Surface Resistance: Exterior</b> (per ANSI/ESD STM11.11)	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>6</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>6</sup> ohms
<b>Surface Resistance: Interior</b> (per ANSI/ESD STM11.11)	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms	1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms
<b>ANSI/ESD S11.4 Level</b>	Level 3	Level 3	Level 3	Level 3 (except Transparency)
<b>Discharge Shielding Energy Test</b> (per ANSI/ESD STM11.31)	<10nJ	<20nJ	<10nJ	<10nJ
<b>Thickness:</b> Typical Value Nominal: ±10% (per MIL-STD-3010C 1003)	0.0028" (0.071mm)	0.0032" (0.0813mm)	0.0030" (0.0762mm)	0.26" (6.6mm)
<b>Puncture Resistance - Average</b> (per MIL-STD 3010C 2065)	12 lbs	22 lbs	10 lbs	15 lbs
<b>Seal Strength</b> (per ASTM D882)	11 lbs, 48 N	15 lbs, 66 N	14 lbs, 62 N	5 lbs, 22 N
<b>Tensile Strength</b> (per ASTM D882)	4600 PSI, 32 MPa	8100 PSI, 55 MPa	4900 PSI, 34 MPa	6469 PSI, 44.57 MPa
<b>Non- corrosive</b> (per FTMS 101C/4046)	Pass	Pass	Pass	Pass
<b>Silicone</b> (ASTM E168)	Not Detected	Not Detected	Not Detected	Not Detected

**Standards:** Meets the requirements of ANSI/ESD S20.20, Packaging Standard, ANSI/ESD S541, and Static Control Bag ANSI/ESD S11.4 level as noted in table above.

See Static Control Bag Storage at [TB-9011](#).

**RoHS 2, REACH, and Conflict Minerals Statement**

None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2015/06/15, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE.  
See [SCS Warranty, Limitation of Liability and Remedies](#)



**Mixed Unsortable Plastic Scrap**

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades.

**SCS bags are recyclable**



926 JR Industrial Drive, Sanford, NC 27332  
Phone: 919-718-0000 | Web: [StaticControl.com](#)

Films are laminated and converted in United States of America

